



December 20, 2021

National Bridge Industrial (S.Z.) Co., Ltd.
% Grace Liu
Consultant
Shenzhen Joyantech Consulting Co. Ltd
1713A, 17th Floor, Block A, Zhongguan Times Square,
Nanshan District
Shenzhen, Guangdong 518000
China

Re: K211750

Trade/Device Name: Disposable Surgical Face Mask, Disposable Surgical Face Mask (Sterile)
Regulation Number: 21 CFR 878.4040
Regulation Name: Surgical apparel
Regulatory Class: Class II
Product Code: FXX
Dated: October 15, 2021
Received: November 22, 2021

Dear Grace Liu:

We have reviewed your Section 510(k) premarket notification of intent to market the device referenced above and have determined the device is substantially equivalent (for the indications for use stated in the enclosure) to legally marketed predicate devices marketed in interstate commerce prior to May 28, 1976, the enactment date of the Medical Device Amendments, or to devices that have been reclassified in accordance with the provisions of the Federal Food, Drug, and Cosmetic Act (Act) that do not require approval of a premarket approval application (PMA). You may, therefore, market the device, subject to the general controls provisions of the Act. Although this letter refers to your product as a device, please be aware that some cleared products may instead be combination products. The 510(k) Premarket Notification Database located at <https://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfpmn/pmnmn.cfm> identifies combination product submissions. The general controls provisions of the Act include requirements for annual registration, listing of devices, good manufacturing practice, labeling, and prohibitions against misbranding and adulteration. Please note: CDRH does not evaluate information related to contract liability warranties. We remind you, however, that device labeling must be truthful and not misleading.

If your device is classified (see above) into either class II (Special Controls) or class III (PMA), it may be subject to additional controls. Existing major regulations affecting your device can be found in the Code of Federal Regulations, Title 21, Parts 800 to 898. In addition, FDA may publish further announcements concerning your device in the Federal Register.

Please be advised that FDA's issuance of a substantial equivalence determination does not mean that FDA has made a determination that your device complies with other requirements of the Act or any Federal statutes and regulations administered by other Federal agencies. You must comply with all the Act's requirements, including, but not limited to: registration and listing (21 CFR Part 807); labeling (21 CFR Part 801); medical device reporting (reporting of medical device-related adverse events) (21 CFR 803) for devices or postmarketing safety reporting (21 CFR 4, Subpart B) for combination products (see <https://www.fda.gov/combination-products/guidance-regulatory-information/postmarketing-safety-reporting-combination-products>); good manufacturing practice requirements as set forth in the quality systems (QS) regulation (21 CFR Part 820) for devices or current good manufacturing practices (21 CFR 4, Subpart A) for combination products; and, if applicable, the electronic product radiation control provisions (Sections 531-542 of the Act); 21 CFR 1000-1050.

Also, please note the regulation entitled, "Misbranding by reference to premarket notification" (21 CFR Part 807.97). For questions regarding the reporting of adverse events under the MDR regulation (21 CFR Part 803), please go to <https://www.fda.gov/medical-devices/medical-device-safety/medical-device-reporting-mdr-how-report-medical-device-problems>.

For comprehensive regulatory information about medical devices and radiation-emitting products, including information about labeling regulations, please see Device Advice (<https://www.fda.gov/medical-devices/device-advice-comprehensive-regulatory-assistance>) and CDRH Learn (<https://www.fda.gov/training-and-continuing-education/cdrh-learn>). Additionally, you may contact the Division of Industry and Consumer Education (DICE) to ask a question about a specific regulatory topic. See the DICE website (<https://www.fda.gov/medical-devices/device-advice-comprehensive-regulatory-assistance/contact-us-division-industry-and-consumer-education-dice>) for more information or contact DICE by email (DICE@fda.hhs.gov) or phone (1-800-638-2041 or 301-796-7100).

Sincerely,

Clarence W. Murray, III, Ph.D.
Assistant Director
DHT4B: Division of Infection Control
and Plastic Surgery Devices
OHT4: Office of Surgical
and Infection Control Devices
Office of Product Evaluation and Quality
Center for Devices and Radiological Health

Enclosure

Indications for Use

510(k) Number (if known)
K211750

Device Name

Disposable Surgical Face Mask
Disposable Surgical Face Mask (Sterile)

Indications for Use (Describe)

The surgical face masks are intended to be worn to protect both the patient and healthcare personnel from transfer of microorganisms, body fluids and particulate material. These masks are intended for use in infection control practices to reduce the potential exposure to blood and body fluids. This is a single use, disposable device, provided non-sterile/sterile.

Type of Use (Select one or both, as applicable)

Prescription Use (Part 21 CFR 801 Subpart D)

Over-The-Counter Use (21 CFR 801 Subpart C)

CONTINUE ON A SEPARATE PAGE IF NEEDED.

This section applies only to requirements of the Paperwork Reduction Act of 1995.

DO NOT SEND YOUR COMPLETED FORM TO THE PRA STAFF EMAIL ADDRESS BELOW.

The burden time for this collection of information is estimated to average 79 hours per response, including the time to review instructions, search existing data sources, gather and maintain the data needed and complete and review the collection of information. Send comments regarding this burden estimate or any other aspect of this information collection, including suggestions for reducing this burden, to:

Department of Health and Human Services
Food and Drug Administration
Office of Chief Information Officer
Paperwork Reduction Act (PRA) Staff
PRASStaff@fda.hhs.gov

"An agency may not conduct or sponsor, and a person is not required to respond to, a collection of information unless it displays a currently valid OMB number."

510(k) Summary**K211750****1. Contact Details****1.1 Applicant information**

Applicant Name	National Bridge Industrial (S.Z.) Co., Ltd.
Address	Phase 2, N.B.I. Building, No. 501-502, Sili Road, Guanlan, Longhua District, Shenzhen, Guangdong, China
Contact person	Yang Haixiong
Phone No.	+86-13502801741
E-mail	sznbi061@nbi.com.cn
Date Prepared	2021-10-14

1.2 Submission Correspondent

 <p>卓远天成</p>	Shenzhen Joyantech Consulting Co., Ltd 1713A, 17th Floor, Block A, Zhongguan Times Square, Nanshan District, Shenzhen, Guangdong Province, China
	<p>Phone No. +86-755-86069197</p> <p>Contact person Grace Liu; Field Fu;</p> <p>Contact person's e-mail grace@cefda.com; field@cefda.com</p> <p>Website http://www.cefda.com</p>

2. Device Information

Trade name	Disposable Surgical Face Mask Disposable Surgical Face Mask (Sterile)
Common name	Surgical Face Mask
Classification name	Mask, Surgical
Review Panel	General Hospital
Product code	FXX
Device Class	II
Regulation No.	21 CFR 878.4040

3. Legally Marketed Predicate Device

Trade Name	Surgical Face Masks (Sterile), Surgical Face Masks (Non-sterile)
-------------------	--

Product: Disposable Surgical Face Mask
 Disposable Surgical Face Mask (Sterile)

Version: A/0

510(k) Number	K202843
Product Code	FXX
Manufacturer	B.J.ZH.F.Panther Medical Equipment Co., Ltd.

4. Device Description

The proposed devices are three-layer, flat pleated masks. A mask is composed of a mask body, a nose piece, two ear loops and two side tapes.

The mask body is manufactured with three layers, the inner layer and the outer layer are made of spunbond polypropylene nonwoven fabric, and the middle layer is made of meltblown polypropylene nonwoven fabric.

The proposed device is held in place over the user's mouth and nose by two elastic ear loops welded to the mask body. The elastic ear loops are knitted elastic loops (made of polyester and spandex).

The nose piece is in the layers of face mask to allow the user to fit the face mask around their nose, which is a iron wire with polypropylene covering.

In order to improve the wearing comfort, two side tapes are welded to the mask body along the width direction to cover the mask edges. The side tapes are made of spunbond polypropylene nonwoven fabric (the same material as the inner layer).

The proposed device contains two models, and the structure, materials and dimensions of the two models are exactly the same except the sterile status. Disposable Surgical Face Mask is provided non-sterile and Disposable Surgical Face Mask (Sterile) is provided sterile. They are both intended to be single use, disposable devices.

The proposed devices can meet the requirements for the performance class of Level 3 specified in ASTM F2100.

5. Intended Use/Indication for Use

The surgical face masks are intended to be worn to protect both the patient and healthcare personnel from transfer of microorganisms, body fluids and particulate material. These masks are intended for use in infection control practices to reduce the potential exposure to blood and body fluids. This is a single use, disposable device, provided non-sterile/sterile.

6. Technological Characteristics Comparison

Comparison item	Proposed Device (K211750)	Predicate Device (K202843)	Comment
Manufacturer	National Bridge Industrial (S.Z.) Co., Ltd.	B.J.ZH.F.Panther Medical Equipment Co., Ltd.	None
Product name	Disposable Surgical Face Mask	Surgical Face Masks (Sterile),	None

	Disposable Surgical Face Mask (Sterile)	Surgical Face Masks (Non-sterile)	
Product Code	FXX	FXX	Same
Regulation Number	21 CFR § 878.4040	21 CFR § 878.4040	Same
Classification	Class II	Class II	Same
OTC use	Yes	Yes	Same
Indications for Use	The surgical face masks are intended to be worn to protect both the patient and healthcare personnel from transfer of microorganisms, body fluids and particulate material. These masks are intended for use in infection control practices to reduce the potential exposure to blood and body fluids. This is a single use, disposable device, provided non-sterile/sterile.	The Surgical Face Mask is intended for single use by operating room personnel and other general healthcare workers to protect both patients and healthcare workers against transfer of microorganisms, blood and body fluids, and particulate materials.	Similar
Mask style	Flat-pleated, 3 layers	Flat-pleated, 3 layers	Same
Design feature	Ear loop	Ear loop/Tie-on	Similar
Single use	Yes	Yes	Same
Color	Blue	Blue	Same
Specifications and dimensions	175mm×95mm: Nose piece: 90mm×3.2mm Ear loop: 160mm×3.5mm	1. 14.5cm×9cm: Nose clip: 85mm×2.9mm Ear loop: 180mm×3mm Ties: 910mm×10mm 2. 17.5cm×9.5cm: Nose clip: 100mm×2.9mm Ear loop: 180mm×3mm Ties: 910mm×10mm	Similar
Sterility	Non-sterile/Sterile	Non-sterile/Sterile	Same
Sterilization method	EO (SAL: 10 ⁻⁶)	EO (SAL: 10 ⁻⁶)	Same
ASTM F2100 Level	Level 3	Level 2	Different Issue 1
Labeling	Complied with 21 CFR part 801	Complied with 21 CFR part 801	Same
Materials			
Outer layer	Spunbond Polypropylene	Spunbond Polypropylene	Different Issue 2
Middle layer	Meltblown Polypropylene	Meltblown Polypropylene	

Inner layer	Spunbond Polypropylene	Spunbond Polypropylene	
Nose piece	Iron wire with polypropylene covering	Medical polypropylene and Q235	
Ear loop	Polyester and spandex	Nylon and spandex	
Side tape	Spunbond Polypropylene	None	
Performances			
/	Disposable Surgical Face Mask	Disposable Surgical Face Mask (Sterile)	Surgical Face Masks (Sterile), Surgical Face Masks (Non-sterile)
Fluid Resistance (ASTM F1862)	Pass at 160mmHg	Pass at 160mmHg	Pass at 120mmHg
Particulate Filtration Efficiency (ASTM F2299)	Average 99.74%	Average 99.63%	Average 98.98%
Bacterial Filtration Efficiency (ASTM F2101)	Average 99.6%	Average 99.8%	Average 98.92%
Differential Pressure (Delta P) (EN 14683)	Average 3.9 mmH ₂ O/cm ²	Average 4.0 mmH ₂ O/cm ²	Average 4.4 mmH ₂ O/cm ²
Flammability (16CFR 1610)	Class 1	Class 1	Class 1
Biocompatibility	ISO 10993-5 and ISO 10993-10; Under the conditions of the study, the proposed device extract was determined to be non-cytotoxic, non-sensitizing, and non-irritating.		ISO 10993-5 and ISO 10993-10; Under the conditions of the study, the proposed device extract was determined to be non-cytotoxic, non-sensitizing, and non-irritating.

Issue 1: The proposed device has conducted the performance testing as per ASTM F2100, the test results showed that the proposed device meet the requirements for Level 3.

Issue 2: The construction materials used are different.

7. Summary of Non-clinical Testing

Non-clinical tests were conducted to verify that the proposed device met all design specifications and acceptance criteria in the standard and test methodology. The tests were conducted according to the following standards, and the results demonstrated that the proposed device complies with the following standards:

- ISO 10993-1:2018 Biological evaluation of medical devices - Part 1: Evaluation and testing within a risk management process
- ISO 10993-5:2009 Biological Evaluation of Medical Devices - Part 5: Tests for in Vitro cytotoxicity
- ISO 10993-10:2010 Biological Evaluation of Medical Devices - Part 10: Tests for irritation and skin sensitization
- ASTM F2100-19 Standard Specification for Performance of Materials Used in Medical Face Masks
- ASTM F1862/F1862M-17 Standard Test Method for Resistance of Medical Face Masks to Penetration by Synthetic Blood (Horizontal Projection of Fixed Volume at a Known Velocity)
- ASTM F2101-19 Standard Test Method for Evaluating the Bacterial Filtration Efficiency (BFE) of Medical Face Mask Materials, Using a Biological Aerosol of Staphylococcus aureus
- EN 14683:2019+AC:2019 Medical Face Masks - Requirements and Test Methods
- ASTM F2299/F2299M-03(R2017) Standard Test Method for Determining the Initial Efficiency of Materials Used in Medical Face Masks to Penetration by Particulates Using Latex Spheres
- 16 CFR 1610 Standard for the Flammability of Clothing Textiles
- ISO 11135:2014 Sterilization of health-care products - Ethylene oxide - Requirements for the development, validation and routine control of a sterilization process for medical devices
- ISO 11737-2:2019 Sterilization of medical devices - Microbiological methods - Part 2 Tests of sterility performed in the definition, validation and maintenance of a sterilization process
- ISO 10993-7:2008 Biological evaluation of medical devices Part 7 Ethylene oxide sterilization residuals
- ASTM F1980-16 Standard Guide for Accelerated Aging of Sterile Barrier Systems for Medical Device
- ASTM F88/F88M-15 Standard Test Method for Seal Strength of Flexible Barrier Materials
- ASTM F1929-15 Standard Test Method for Detecting Seal Leaks in Porous Medical Packaging by Dye Penetration
- ASTM F1886M-2016 Standard Test Method for Determining Integrity of Seals for Flexible Packaging by Visual Inspection

Table 2 Performance Testing

Test	Purpose	Acceptance Criteria per ASTM F2100-19 (AQL=4.0%)	Results (Statistics of three lots, 32 per lot)	
			Disposable Surgical Face Mask	Disposable Surgical Face Mask (Sterile)
Fluid	Verify the fluid	Pass at 160	96 out of 96 pass at	96 out of 96 pass at

Resistance (ASTM F1862)	resistance of the proposed device can meet the requirements for Level 3 specified in ASTM F2100-19.	mmHg	160 mmHg	160 mmHg
Bacterial filtration efficiency (BFE) (ASTM F2101)	Verify the bacterial filtration efficiency of the proposed device can meet the requirements for Level 3 specified in ASTM F2100-19.	≥98%	99.5%~99.7% (Average: 99.6%)	99.7%~99.9% (Average: 99.8%)
Particulate filtration efficiency (PFE) (ASTM F2299)	Verify the particulate filtration efficiency of the proposed device can meet the requirements for Level 3 specified in ASTM F2100-19.	≥98%	99.37%~99.99% (Average: 99.74%)	99.32%~99.85% (Average: 99.63%)
Differential pressure (Delta-P) (EN 14683)	Verify the differential pressure of the proposed device can meet the requirements for Level 3 specified in ASTM F2100-19.	<6.0 mmH ₂ O/cm ²	(3.4~4.2) mmH ₂ O/cm ² (Average: 3.9 mmH ₂ O/cm ²)	(3.5~4.5) mmH ₂ O/cm ² (Average: 4.0 mmH ₂ O/cm ²)
Flammability (16 CFR 1610)	Verify the flammability of the proposed device can meet the requirements for Level 3 specified in ASTM F2100-19.	Class 1	Class 1	Class 1

Table 3 Biocompatibility Testing

Test	Purpose	Acceptance Criteria	Result
In vitro Cytotoxicity (ISO 10993-5)	Verify that the proposed device extract is non-cytotoxic.	The extract is non-cytotoxic under the research conditions.	Pass
Skin Irritation (ISO 10993-10)	Verify that the proposed device extract is non-irritating.	The polar and non-polar extracts are non-irritating under the research conditions.	Pass

Skin Sensitization (ISO 10993-10)	Verify that the proposed device extract is non-sensitizing.	The polar and non-polar extracts are non-sensitizing under the research conditions.	Pass
--------------------------------------	---	---	------

8. Clinical testing

Clinical testing was not performed for the proposed device.

9. Conclusion

The nonclinical tests demonstrate that the proposed device is as safe, as effective, and performs as well as or better than the legally marketed device (K202843).